

MOLYKOTE® HP-500 Grease

Fully fluorinated grease that provides extraordinary performance under extreme conditions

Features & benefits

- Compatible with most plastics
- Excellent stability at high temperatures
- Superior resistance to chemicals and solvents
- Minimal deterioration due to oxidation; appropriate for long-term lubrication
- Low vapor pressure (base oil)

Composition

- Perfluoropolyether
- Fluorinated polymer

Applications

MOLYKOTE® HP-500 Grease can be used broadly under harsh conditions, such as high temperatures, corrosive, solvents, liquefied natural gasses, high vacuum, etc. Can be used in cleanroom equipment and semiconductor manufacturing equipment where the vaporization of the lubricating material is undesirable.

Description

MOLYKOTE® HP-500 Grease is a perfluoropolyether (PFPE)-based grease thickened with polytetrafluoroethylene (PTFE); it is useful for reducing wear in many plastic-on-plastic applications.

How to use

Clean point of application. As is usual with lubricating greases, apply or fill by means of a brush, spatula, or automatic lubrication device.

Handling precautions

Although MOLYKOTE® HP-500 Grease is highly chemically stable, at temperatures in excess of 250°C, the material will gradually decompose and release toxic gases; be sure to have adequate ventilation if you expect the material to decompose. Do not smoke cigarettes that are contaminated with this product. Be sure to wash hands thoroughly after use.

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER

Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard ⁽¹⁾	Test	Unit	Result
	Appearance		White
JIS K 2220	Penetration (worked 60 times)	mm/10	280
	NLGI class		2
	Service temperature range	°C	-20 to 200
	Density	g/cm ³	2.0
MIL-S-8660	Bleed (200°C, 24 hours)	%	0-4
MIL-S-8660	Evaporation (200°C, 24 hours)	%	0-1
MIL-S-8660	Evaporation (200°C, 1,000 hours)	%	0.8
ASTM D2596	Four ball weld load (1,500 rpm/1 minute)	N	3,440
ASTM D2266	Four ball wear scar (1,200 rpm, 392 N, 1 hour)	mm	0.9
JIS K 2220	Low-temperature torque test (-20°C)		
	Starting torque	Ncm	34
	Running torque	Ncm	18
JIS K 2220	Low-temperature torque test (-40°C)		
	Starting torque	Ncm	Not measurable
	Running torque	Ncm	Not measurable
	Base oil vapor pressure 20°C	Pa	1.33x10 ⁻⁶

⁽¹⁾JIS: Japanese Industrial Standard. MIL: Military Specification and Standards. ASTM: American Society for Testing and Materials.

LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

Usable life and storage

When stored, unopened, in a cool, dark place, this product has a usable life of 36 months from the date of production.

Packaging

This product is available in 100 g and 500 g plastic cans.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.
© 2002-2019 DuPont.*

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.